

401 COLORS

SIDING • WINDOWS • GUTTERS

Colors:
Various Colors -
Part Number
Beginning With
04273+



- Plastic cartridge
- One year shelf life
- Paintable
- Will not crack & yellow
- Mildew Resistant
- Available in 400+ Colors that match all the major Window & Siding colors.
- Solvent Free
- VOC compliant in all 50 states
- Minimal Odor
- 4 inch nozzle for hard to reach areas
- Interior & Exterior Applications

THE IDEAL SEALANT/ADHESIVE FOR:

- Siding
- Gutters
- Glass
- Windows
- Fiber Cement
- Aluminum
- Concrete
- Crown Molding
- Stucco
- Brick
- Wood
- And more...

Visit Our Website for Other
BOSS[®] MADE TO WORK Products
www.bossproducts.com

BOSS[®] 399 Neutral Cure Silicone Glazing Sealant

BOSS[®] 400 Colors Siding, Window & Metal Roof Sealant

BOSS[®] 380 Contractor's RTV Silicone Adhesive/Sealant

BOSS[®] 125 Multi-Seal[®] Roofing, Gutter, Concrete, Construction Sealant

Call The **BOSS[®]** 800-928-BOSS
Soudal Accumetric

350 Ring Road • Elizabethtown • KY 42701

(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412



401 COLORS

SIDING • WINDOWS • GUTTERS

TYPICAL PROPERTIES

Weight per gallon, approximate (colors).....	12.2 lb./gal.
Weight per gallon, approximate (clear).....	8.85 lb./gal.
% Volume Shrinkage: ASTM C-733-87.....	28%
pH.....	7.8 – 8.2
Tack-Free Time: ASTM D-2377-84.....	<25 minutes
Weather Resistance: ASTM C-732-82.....	No washout, discoloration, loss of adhesion or cracking after 500 hours weathering
Peel Strength:	
Wood.....	26.0 pounds-force
Glass.....	29.0 pounds-force
Aluminum.....	32.0 pounds-force
Low Temperature Flexibility ASTM C-734-82.....	No cracking through to substrate or adhesion loss
Extrudability after Package Aging (freeze-thaw stability):	
ASTM C-731-87.....	17.2 grams/second
Volatile Organic Content (VOC-minus water):	
Colors.....	13.7 grams/liter
Clear.....	10.5 grams/liter
Service Temperature.....	-20°F to 185°F
Application Temperature.....	40°F to 110°F

Information on this data sheet is subject to change without notice and should not be used for writing specifications. For additional information on specific applications, contact Soudal Accumetric.

LIMITATIONS

- Do not use for structural glazing
- It is the sole responsibility of the user to test the adhesion to the substrate for suitability

CAUTION

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Safety Data Sheet (SDS).

Call The **BOSS[®]** 800-928-BOSS

Soudal Accumetric

350 Ring Road • Elizabethtown • KY 42701

(270) 769-3385 • 800-928-BOSS • Fax: (270) 765-2412

www.bossproducts.com

