

ALUMINUM COMPLEX & CALCIUM SULFONATE GREASES

THICKENER TYPE: ALUMINUM COMPLEX



THERMAPLEX® AQUA BEARING GREASE



- Excellent resistance to fresh and salt water
- Resists water washout
- Good adhesion properties
- Excellent corrosion resistance
- Significant load carrying capability
- Reduces wear
- Reduces grease consumption
- Greater degree of bearing protection

PROPERTIES:

Appearance: Amber colored paste
Temperature Range: -4°F (-20°C) to 302°F (150°C)
Dropping Point: 500°F (260°C)
4-Ball Weld Load: >315 kg.
Timken "OK" Load: 50 lbs.

For Base Oil Viscosity Download TDS from www.lpslabs.com

NET CONTENTS	CONTAINER	LPS #
14.1 oz. (400 g)	cartridges	70514

THICKENER TYPE: CALCIUM SULFONATE



THERMAPLEX® CS MOLY BEARING GREASE



- Enhanced with molybdenum disulfide
- Reduces wear from vibration
- Prolongs bearing life
 - Outstanding extreme pressure (EP) performance
 - Superior rust and corrosion protection - Perfect score on the EMCOR rust test
 - Exceptional water resistance
- Multi-application bearing grease
- Extends relubrication intervals for bearings
- Excellent oxidation stability
- Nonfood Compounds Program Listed Category Code: H2 Registration #142214

PROPERTIES:

Appearance: Gray/Black colored paste
Temperature Range: 0°F (-18°C) to 425°F (218°C)
Dropping Point: 570°F (300°C)
4-Ball Weld Load: >600 kg.
Timken "OK" Load: 65 lbs.

For Base Oil Viscosity Download TDS from www.lpslabs.com

NET CONTENTS	CONTAINER	LPS #
14.1 oz. (400 g)	cartridges	70814

AEROSOL GREASES

THICKENER TYPE: INORGANIC (NON-MELTING)



RED & REDI MULTI-PURPOSE RED GREASE



- Delivers excellent non-sling lubrication
- Prevents rust, corrosion, and oxidation
- Red color allows easy visual inspection
- Remains effective at extremely high temperatures 450°F (232°C)
- Penetrates quickly
- Reduces friction and vibration

NET CONTENTS	CONTAINER	LPS #
11 wt. oz./312 g/451 mL	aerosol	05816

PROPERTIES:

Appearance: Red
Temperature Range: -22°F (-30°C) to 450°F (232°C)
Dropping Point: 550°F (288°C)
4-Ball Weld Load: >250 kg.
Timken "OK" Load: 30 lbs.

For Base Oil Viscosity Download TDS from www.lpslabs.com

THICKENER TYPE: LITHIUM COMPLEX



WHITE LITHIUM GREASE WITH PTFE



- Rapidly forms into a pure white grease that will not melt or wash away
- Provides maximum lubrication
- Rust and oxidation inhibitors protect metal
- Pure white color allows easy visual inspection
- Heat and water-resistant
- Acceptable for use in Canadian Food Processing Establishments

NET CONTENTS	CONTAINER	LPS #
10 wt. oz./284 g/418 mL	aerosol	03816

PROPERTIES:

Appearance: White
Temperature Range: 5°F (-15°C) to 290°F (143°C)
Dropping Point: 350°F (177°C)
4-Ball Weld Load: >315 kg.
Timken "OK" Load: 45 lbs.

For Base Oil Viscosity Download TDS from www.lpslabs.com